



SABIC® LDPE 2015T

Low density polyethylene for masterbatch compounding

Description

SABIC® LDPE 2015T is an additive free standard CTR® tubular grade for masterbatch with a high purity and a medium viscosity.

Application

SABIC® LDPE 2015T is very suitable for masterbatches in film applications, with a very high carbon black, titanium dioxide or pigment loading.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

Typical data.

			Revision
Properties	Units SI	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 190 °C and 2.16 kg	dg/min	15	ISO 1133
Density	kg/m ³	920	ISO 1183
Thermal properties			
Vicat softening temperature at 10 N (VST/A)	°C	85	ISO 306
DSC test			DIN 53765
melting point	°C	108	
enthalpy change	J/g	105	



SABIC® LDPE 2015T

Low density polyethylene for masterbatch compounding

General information. SABIC Europe produces low density polyethylene by SABIC's CTR® tubular reactor process. SABIC® LDPE grades for masterbatch are available in a wide range of melt flow rates. All grades are characterized by their good basic stability. They do not contain any catalyst, residues or additives. The grades are very homogeneous materials of high constant quality. SABIC® LDPE grades with their variety of viscosities are very suitable for both additives, black, white and colour masterbatches with varying amounts of additives and/or pigments (good wettability). SABIC® LDPE has a good compatibility with other polyethylenes and polyethylene copolymers. So masterbatches based on SABIC® LDPE will have good distribution in various polyethylene media.

Health, Safety and Food Contact regulations. Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet (www.SABIC-europe.com). Additional specific information can be requested via your local Sales Office.

Quality. SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO 9001. It is SABIC Europe's policy to supply materials that meet customers specifications and needs and to keep up its reputation as a pre-eminent, reliable supplier of e.g. polyethylenes.

Storage and handling. Polyethylenes resins (in pelletised or powder form) should be stored in such a way that it prevents exposure to direct sunlight and/or heat, as this may lead to quality deterioration. The storage location should also be dry, dust free and the ambient temperature should not exceed 50 °C. Not complying with these precautionary measures can lead to a degradation of the product which can result in colour changes, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletised or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

Environment and recycling. The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC Europe considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC Europe whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.