

## PERFORMANCE CHEMICALS

# SABIC™ PMMA 23SP

Polymethyl Methacrylate Acrylic

# PRODUCT DESCRIPTION:

SABIC™ PMMA 23SP is a special extrusion grade with good chemical resistance and weather resistance. The grade is available in pellet form.

## **CHARACTERISTICS:**

SABIC™ PMMA 23SP has the following:

- High clarity
- Good chemical resistance
- Good impact resistance
- Good toughness
- High gloss

#### **TYPICAL DATA:**

PHYSICAL PROPERTIES	Unit	Typical Value (1)	Test Method
Specific gravity	g/cm3	1.19	ISO 1183
Total light transmittance	%	93	ISO 13468
Haze	%	0.3	ISO 14782
Refractive index	-	1.49	ASTM D 542/ISO489
Water adsorption	%	0.3	ISO 62
THERMAL PROPERTIES	Unit	Typical Value (1)	<b>Test Method</b>
Specific heat	J/(g°C)	1.5	JIS K 7123
Coefficient of linear expansion	J/°C	6x10 <sup>-5</sup>	ASTM D 696
Coefficient of thermal conductivity	W/(m°C)	0.2	ASTM C 177
Deflection temperature under load	°C	93	ISO 75
Vicat softening temperature	°C	100	ISO 306
Melt flow rate	g/10min	2.3	ISO 1133
MECHANICAL PROPERTIES	Unit	Typical Value (1)	Test Method
Tensile Strength	MPa	75	ISO 527
Tensile Elongation	%	7	ISO 527
Modulus Of elasticity	GPa	3.3	ISO 527
Flexural Strength	MPa	135	ISO 178
Flexural Modulus	GPa	3.3	ISO 178
Charpy Impact strength (un notched	KJ/m2	20	ISO 179
Charpy Impact strength (Notched)		1.4	ISO 179
Rockwell Hardness	KJ/m2	95	ISO 2039
ELECTRICAL PROPERTIES	Unit	Typical Value (1)	Test Method
Surface Resistivity	Ω	>10 <sup>16</sup>	JIS K 6911
Volume Resistivity	$\Omega$ m	>10 <sup>13</sup>	JIS K 6911
Dielectric strength	MV/m	20	JIS K 6911
Dielectric constant	-	3.70	JIS K 6911
Power factor	-	0.050	JIS K 6911

<sup>(1)</sup> Typical values; not to be construed as specification limits.

#### **PACKING & STORAGE:**

Handle in an area equipped with local or general ventilation. Provide facilities for washing eyes and body in case of emergency near the handling area. As preventive measure, make sure all equipment and devices are properly grounded. Store at a location away from heat and fire source and an area not exposed to sunlight. Store in an area where no water leakage occurs and the humidity is low.

#### **CONTACT US:**

Saudi Basic Industries Corporation P.O. Box 5101 Riyadh 11422 Kingdom of Saudi Arabia Tel: 966 11 2258000

Tel: 966 11 2258000 Fax: 966 11 2259000

Technical Marketing
Tel: 966 11 2258630
Fax: 966 11 2258730
Email: fp\_pcsbu@sabic.com
Website: www.sabic.com

Application Development (SPADC)

Tel: 966 11 2501948 Email: fp\_pcsbu@sabic.com Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.

DISCLAIMER: Products referred to in this document are sold subject to SABIC's Standard Terms and Conditions of Sale (the "Terms") which are available upon request. The information contained herein is supported by research and is believed to be reliable as of the date compiled and representative of production but no guarantee, representation or warranty, express or implied, is made or intended as to the correctness, sufficiency, suitability, merchantability or fitness for a particular purpose of any such information or the products to which it relates. Users are solely responsible for making their own determination as to the suitability of any product for their intended use and that such use is in compliance with applicable laws and standards. Nothing in this document is intended or should be construed to grant a license or immunity under any SABIC or third party intellectual property rights. Save and as expressly set out in the Terms, SABIC shall in no event be liable for any loss, damage or injury howsoever arising from the use of information or the products referred to herein.