

POLYMERS

# SABIC® PS 330

## High Impact Polystyrene for Sheet Extrusion

### Product Description

High Impact Polystyrene PS 330 is manufactured by continuous mass polymerization of styrene monomer. An elastomer is incorporated during polymerization to achieve impact resistance property. It is generally opaque in color. It is a high impact strength polystyrene with high heat deflection temperature and good physical properties.

### Typical Applications

It is primarily designed for extrusion and thermoforming applications. It can be used for food packaging and dairy products.

### Processing Conditions

Typical temperature (°C) profile for PS 330:

Throat	Feed	Transition	Metering	Die
Ambient	185	195	205	215

### Typical data

Properties	Unit	Value (1)	Test Method
Melt Flow Rate @ 230°C & 2.16 kg Load	g/10 min.	4.0	D-1238
Density @ 23°C	kg/m <sup>3</sup>	1040	D-792
Bulk Density (Method B)	kg/m <sup>3</sup>	600	D-1895
<b>Mechanical Properties(2)</b>			
Tensile Strength	MPa	29	D-638
Tensile Elongation	%	50	D-638
Tensile Modulus	MPa	2353	D-638
Flexural Strength	MPa	44	D-790
Flexural Modulus	MPa	2647	D-790
Izod Impact Notched @ 23°C	J/m	110	D-256
Rockwell Hardness, L-Scale	-	67	D-785
M-Scale	-	10	-
<b>Thermal Properties</b>			
Vicat Softening Point (Rate A, 1 Kg/50°C)	°C	99	D-1525
Heat Deflection Temperature (Method B, 455 KPa, Annealed)	°C	97	D-648
Flammability Rating, UL 94 @ 1.3 mm and 3 mm (natural color)	Class	HB	-

(1) Typical values; not to be construed as specification limits.

(2) Based on Injection molded specimens.

## Food Regulation

PS 330 is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

## Storage and Handling

Polystyrene resin should be stored to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PS resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O. Box 5101, Riyadh 11422, Kingdom of Saudi Arabia  
Tel: 966 1 2258000  
Fax: 966 1 2259000

Technical Marketing  
Tel: 966 1 2659166  
Fax: 966 1 2653544  
Website: [www.sabic.com](http://www.sabic.com)

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.