





PP Homopolymer for Raffia applications

# **Product Description**

PP 504P is specially developed for producing stretched tapes with following features.

- Consistent processability
- Easy orientation
- Low water carry over
- Good mechanical properties

# **Typical Applications**

PP 504P can be used for producing woven bags, flexible intermediate bulk containers, ropes & twines, carpet backing, cable fillers and geotextiles.

## **Typical data**

Properties	Unit	Value (1)	ASTM Method
Resin Properties			
Melt Flow Rate @ 230°C & 2.16 kg load Density @ 23°C	g/10 min. kg/m <sup>3</sup>	3.2 905	D 1238 D 792
Mechanical Properties <sup>(2)</sup>			
Tensile Strength @ Yield	MPa	35	D 638
Tensile Elongation @ Yield	%	12	D 638
Flexural Modulus (1% Secant)	MPa	1450	D 790A
Notched Izod Impact Strength @ 23°C	J/m	55	D 256
Rockwell Hardness, R-Scale	-	102	D 785
Thermal Properties <sup>(2)</sup>			
Vicat Softening Point	°C	156	D 1525B
Heat Deflection Temperature @ 455 KPa	°C	94	D 648
(1) Truniant values, not to be construed as energification limits			

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens.

# **Processing Conditions**

Barrel temperature range: 230 - 260°C

## Food Regulation

L

PP 504P is suitable for food contact application. Detailed information is provided in the relevant Safety Data Sheet and for additional specific information please contact SABIC local representative for certificate.

## Storage and Handling

PP resin should be stored to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia Tel: 966 1 2258000 Fax: 966 1 2259000

Technical Marketing Tel: 966 1 2659166 Fax: 966 1 2653544 Toll-free 800 1245577

PP Sales: Fax: 966 1 2258771 Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.