



## SABIC® PP 510P

### PP homopolymer for Fibre, filament and tape extrusion

**Description:**

SABIC® PP 510P is a fibre grade with an anti gas fading stabilisation package. This grade is suitable for e.g. wipes and industrial carpets.

**Application:**

SABIC® PP 510P is suitable for spinning of coarse staple fibres, carpet fibres and yarns and geotextiles with moderate tenacity.

**Health, Safety and Food Contact regulations:**

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

IMDS 7172624

**Typical values**

Revision 20140109

Properties	Unit (SI)	Values	Test methods
<b>Polymer properties</b>			
<b>Melt flow rate (MFR)</b> at 230 °C and 2.16 kg	dg/min	<b>12</b>	ISO 1133
<b>Density</b>	kg/m <sup>3</sup>	<b>905</b>	ISO 1183
<b>Molecular Weight Distribution</b>	-	<b>Broad</b>	-
<b>Isotacticity</b>	-	<b>Medium</b>	-
<b>Formulation</b>			
<b>Gas fading stabilized</b>	-	<b>Yes</b>	-
<b>Mechanical properties</b>			
<b>Tensile test</b>			ISO 527-2 1A
stress at yield	1) MPa	<b>35</b>	
strain at yield	1) %	<b>11</b>	
tensile modulus	2) MPa	<b>1700</b>	

1) Speed of testing: 50 mm/min

2) Speed of testing: 1 mm/min



## SABIC® PP 510P

### PP homopolymer for Fibre, filament and tape extrusion

**Quality:**

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

**Storage and handling:**

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

**Disclaimer.** The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.