



SABIC® PP 521P

PP homopolymer for Bi-axially oriented film

Description:

SABIC® PP 521P is particularly designed for (biaxially) oriented PP film extrusion with a very specific molecular structure providing the ultimate properties required for the stretching process.

Application:

SABIC® PP 521P is typically used in mono layer or coextruded (B)OPP film. SABIC®PP 521P is known for its excellent Metallisation behaviour.

Health, Safety and Food Contact regulations:

SABIC®PP 521P has a Food Contact Declaration. Material Safety Data Sheets (MSDS) and Product Safety Declarations are available on our Internet site <http://www.sabic-europe.com>.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

IMDS 7172624

Typical values

Revision 20121203

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	3	ASTM D 1238
Density	kg/m ³	905	ASTM D 792
Molecular Weight Distribution	-	Broad	-
Isotacticity	-	Medium	-
Formulation			
Anti block agent	-	No	-
Slip agent	-	No	-
Mechanical properties			
Tensile test			ASTM D 638
stress at yield	1) MPa	35	
strain at yield	1) %	10	
secant modulus at 1% elongation	2) MPa	1550	
Thermal properties			
Vicat softening temperature	3)		ASTM D 1525
at 10 N (VST/A)	°C	152	
at 50 N (VST/B)	°C	88	

1) Speed of testing: 50 mm/min

2) Speed of testing: 1 mm/min

3) Temperature rate: 120°C/h



SABIC® PP 521P

PP homopolymer for Bi-axially oriented film

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.