



# **SABIC® PP 525P**

## PP homopolymer for Thermoforming

### **Description:**

SABIC® PP 525P is a medium flow material typically used in extrusion applications like sheet and thermoforming.

### Application:

SABIC® PP 525P is typically used in dairy, flower pots, yellow fats and disposables plates and cups. However, customers use this grade also in combination with fillers like Talc and CaCO3.

### Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site http://www.SABIC-europe.com

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com)

IMDS 7172624

**Typical values** Revision 20140109

Typical values				1(6)131011 201 1010
Properties		Unit (Si)	Values	Test methods
Polymer properties				
Melt flow rate (MFR)				ISO 1133
at 230 °C and 2.16 kg		dg/min	3.0	
Density		kg/m³	905	ISO 1183
Molecular Weight Distribution		-	Broad	-
Isotacticity		-	Medium	-
Formulation				
Anti static agent		-	No	-
Nucleating agent		-	No	-
Mechanical properties				
Tensile test				ISO 527-2 1A
stress at yield	1)	MPa	37	
strain at yield	1)	%	10	
tensile modulus	2)	MPa	1550	
Izod impact notched				ISO 180/1A
at 23 °C		kJ/m²	3.5	
Charpy impact notched				ISO 179/1eA
at 23 °C		kJ/m²	4.5	
Thermal properties				
Heat deflection temperature	3)			ISO 75
at 1.80 MPa (HDT/A)		°C	55	
at 0.45 MPa (HDT/B)		°C	85	
Vicat softening temperature	4)			ISO 306
at 10 N (VST/A)		°C	152	
at 50 N (VST/B)		°C	88	

<sup>1)</sup> Speed of testing: 50 mm/min

internet www.sabic-europe.com

<sup>2)</sup> Speed of testing: 1 mm/min

<sup>3)</sup> Flat wise ( testbar 80\*10\*4mm)4) Temperature rate: 120°C/h

Temperature rate: 120°C/h





# **SABIC® PP 525P**

## PP homopolymer for Thermoforming

#### Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

#### Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

**Disclaimer.** The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.