



SABIC® PP 578N

PP homopolymer for Injection moulding

Description:

SABIC® PP 578N is a nucleated PP homopolymer grade. This grade allows for cost efficient processing on the basis of good flow behavior, short cycle times, and robust processing behaviour. Products made from SABIC® PP 578N typically have low warpage, high stiffness in combination with moderate impact strength at room temperature, and a high gloss.

Application:

SABIC® PP 578N is typically used in domestic appliances and furniture, even as replacement for talcum or chalk filled compounds.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.

This grade material is UL registered under File E111275 (www.ul.com) / IMDS 7172624

Typical values

Revision 20140109

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	dg/min	25	ISO 1133
Density	kg/m ³	905	ISO 1183
Formulation			
Anti static agent	-	No	-
Nucleating agent	-	Yes	-
Mechanical properties			
Tensile test			ISO 527-2 1A
stress at yield	1) MPa	38	
strain at yield	1) %	8	
tensile modulus	2) MPa	1900	
Izod impact notched at 23 °C			ISO 180/1A
	kJ/m ²	3.0	
Charpy impact notched at 23 °C			ISO 179/1eA
	kJ/m ²	4.0	
Hardness Shore D	-	72	ISO 868
Thermal properties			
Heat deflection temperature	3)		ISO 75
at 1.80 MPa (HDT/A)	°C	60	
at 0.45 MPa (HDT/B)	°C	95	
Vicat softening temperature	4)		ISO 306
at 10 N (VST/A)	°C	154	
at 50 N (VST/B)	°C	99	

- 1) Speed of testing: 50 mm/min
- 2) Speed of testing: 1 mm/min
- 3) Flat wise (testbar 80*10*4mm)
- 4) Temperature rate: 120°C/h



SABIC® PP 578N

PP homopolymer for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.