

PERFORMANCE CHEMICALS

SABIC™ POM 90S

Polyoxymethylene

PRODUCT DESCRIPTION:

SABIC™ POM 90S is a medium molecular weight grade suitable for Injection molding applications for parts requiring high rigidity and strength for many applications.

CHARACTERISTICS:

SABIC™ POM 90S has the following:

- High toughness and strength.
- Good chemical resistance to solvent.
- High resistance to thermal and oxidative degradation.
- Fuel, strong alkalis as well as good hydrolysis resistance.

TYPICAL DATA:

PHYSICAL PROPERTIES	Unit	Typical Value ⁽¹⁾	Test Method
Density	kg/m ³	1410	ISO 1183
Melt volume rate (MVR)	cm ³ /10min	8	ISO 1133
MVR test temperature	°C	190	ISO 1133
MVR test load	kg	2.16	ISO 1133
Mold shrinkage - parallel	%	2	ISO 294-4
Mold shrinkage - normal	%	1.8	ISO 294-4
Water absorption (23°C-sat)	%	0.65	ISO 62
THERMAL PROPERTIES	Unit	Typical Value ⁽¹⁾	Test Method
Melting temperature (10°C/min)	°C	166	ISO 11357-1,-2,-3
DTUL @ 1.8 MPa	°C	104	ISO 75-1/-2
Coeff.of linear therm. expansion (parallel)	E-4/°C	1.1	ISO 11359-2
MECHANICAL PROPERTIES	Unit	Typical Value ⁽¹⁾	Test Method
Tensile modulus (1mm/min)	MPa	2850	ISO 527-2/1A
Tensile stress at yield (50mm/min)	MPa	64	ISO 527-2/1A
Tensile strain at yield (50mm/min)	%	9	ISO 527-2/1A
Nominal strain at break (50mm/min)	%	30	ISO 527-2/1A
Tensile creep modulus (1h)	MPa	2500	ISO 899-1
Tensile creep modulus (1000h)	MPa	1300	ISO 899-1
Flexural modulus (23°C)	MPa	2700	ISO 178
Charpy impact strength @ 23°C	kJ/m ²	180	ISO 179/1eU
Charpy impact strength @ -30°C	kJ/m ²	160	ISO 179/1eU
Charpy notched impact strength @ 23°C	kJ/m ²	6.5	ISO 179/1eA
Charpy notched impact strength @ -30°C	kJ/m ²	6	ISO 179/1eA
ELECTRICAL PROPERTIES	Unit	Typical Value ⁽¹⁾	Test Method
Relative permittivity - 100 Hz	-	4	IEC 60250
Relative permittivity - 1 MHz	-	4	IEC 60250
Dissipation factor - 100 Hz	E-4	15	IEC 60250
Dissipation factor - 1 MHz	E-4	50	IEC 60250
Volume resistivity	Ohm*m	1E12	IEC 60093
Surface resistivity	Ohm	1E14	IEC 60093
Electric strength	kV/mm	35	IEC 60243-1
Comparative tracking index CTI	-	600	IEC 60112

(1) Typical values; not to be construed as specification limits.

PROCESS GUIDELINES:

Injection Molding

Standard injection molding machines with three phase (15 to 25D) plasticizing screws will fit.

Melt Temperature 190 – 230 °C

Mould Temperature 80 – 120 °C

Film Extrusion

Standard Extruder with grooved feed zone and short compression screw (minimum 25 D) will fit.

Melt Temperature 180 – 190 °C

Other Extrusion

Standard Extruder with grooved feed zone and short compression screw (minimum 25 D) will fit.

Melt Temperature 180 – 190 °C

Sheet Extrusion

Standard Extruder with grooved feed zone and short compression screw (minimum 25 D) will fit.

Melt Temperature 180 – 190 °C

CONTACT US:

Saudi Basic Industries Corporation

P.O. Box 5101

Riyadh 11422

Kingdom of Saudi Arabia

Tel: 966 11 2258000

Fax: 966 11 2259000

Technical Marketing

Tel: 966 11 2258630

Fax: 966 11 2258730

Email: fp_pcsbu@sabic.com

Website: www.sabic.com

Application Development (SPADC)

Tel: 966 11 2501948

Email: fp_pcsbu@sabic.com

Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.

DISCLAIMER: Products referred to in this document are sold subject to SABIC's Standard Terms and Conditions of Sale (the "Terms") which are available upon request. The information contained herein is supported by research and is believed to be reliable as of the date compiled and representative of production but no guarantee, representation or warranty, express or implied, is made or intended as to the correctness, sufficiency, suitability, merchantability or fitness for a particular purpose of any such information or the products to which it relates. Users are solely responsible for making their own determination as to the suitability of any product for their intended use and that such use is in compliance with applicable laws and standards. Nothing in this document is intended or should be construed to grant a license or immunity under any SABIC or third party intellectual property rights. Save and as expressly set out in the Terms, SABIC shall in no event be liable for any loss, damage or injury howsoever arising from the use of information or the products referred to herein.

© 2012 Saudi Basic Industries Corporation. SABIC and the SABIC emblem are trademarks of Saudi Basic Industries Corporation or its affiliates.