

POLYMERS

SABIC[®] HDPE Blow molding B5429

Series

PRODUCT DESCRIPTION

B5429 Series grades are medium molecular weight High Density Polyethylene copolymer. They are primarily intended for blow molding articles of small sizes. B5429 series grades offer excellent combination of toughness, stress cracking resistance, load bearing strength with easy processability. The grade available with antistatic additive is B5429A.

TYPICAL APPLICATIONS

B5429 series grades are classified as multipurpose blow molding grades. They may be blow molded into containers for household and industrial chemicals (eg. Detergents, bleach, fabric softeners, solvents, paints etc), automotive supplies, foodstuffs, toiletries and cosmetics . They can also be used in other hollow thin-walled parts and profile extrusions.

TYPICAL DATA

PROPERTIES	Unit	Value ⁽¹⁾	Test Method
Melt Flow Rate			
@ 190°C & 2.16 kg load	g/10 min	0.3	ASTM D 1238
@ 190°C & 21.6 kg load		29	
Density @ 23°C	Kg/m ³	954	ASTM D 1505
MECHANICAL PROPERTIES ⁽²⁾			
1% Secant Modulus	MPa	1050	ASTM D 638
Tensile Strength @ Yield	MPa	28	ASTM D 638
Tensile Strength @ Break	MPa	19	ASTM D 638
Tensile Elongation @ Break	%	>500	ASTM D 638
Flexural Strength	MPa	25	ASTM D 790
Flexural Modulus	MPa	1000	ASTM D 790
Izod Impact	J/m	180	ASTM D 256
Hardness (Shore D)	-	65	ASTM D 2240
ESCR (100% Igepal), F50	Hrs	100	ASTM D 1693B
ESCR (10% Igepal), F50	Hrs	60	
THERMAL PROPERTIES			
Vicat Softening Point	°C	124	ASTM D 1525
Brittleness Temperature	°C	< -75	ASTM D 746

(1) Typical values: not to be construed as specification limits.

(2) Based on compression molded sheet.

Processing Conditions:

Typical processing conditions for B5429 are:

Barrel temperature: 170-200°C

Melt temperature: 190-220°C

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, Additional specific information can be requested via your local Sales Office.

STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation,
P.O.Box 5101, Riyadh 11422,
Kingdom of Saudi Arabia
Tel: 966 11 2258000
Fax: 966 11 2259000
Website: www.sabic.com

Technical Marketing
Tel: 966 11 2503093

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.

© 2013 Copyright by SABIC. All rights reserved