

### DOMAMID® 66G30VOEF

Polyamide 66, 30%glass fibre reinforced, flame retardant, halogen and red phosphorous free, for injection moulding.

26.04.2010

TYPICAL PROPERTIES	CONDITION	STANDARD	UNIT	VALUE
<b>PHYSICAL</b>				
Density		ISO 1183	[g/cm <sup>3</sup> ]	1,39
<b>MECHANICAL</b>				
Tensile modulus	1 mm/min	ISO 527	[MPa]	9000
Tensile stress at break	5 mm/min	ISO 527	[MPa]	125
Tensile strain at break	5 mm/min	ISO 527	[%]	2,5
Izod impact notched	+23 °C	ISO 180/1A	[kJ/m <sup>2</sup> ]	7
Hardness Rockwell		ISO 2039/2	[ScaleR]	120
<b>THERMAL</b>				
Melting point	DSC	ISO 11357-1	[°C]	260 ± 2
Heat Deflection Temperature (HDT-B)	0,45 MPa	ISO 75	[°C]	250
Heat Deflection Temperature (HDT-A)	1,80 MPa	ISO 75	[°C]	235
VICAT softening temperature	50°C/h - 50N	ISO 306	[°C]	250
<b>ELECTRICAL</b>				
Volume resistivity		IEC 93	[Ω·cm]	10 <sup>15</sup>
Surface resistivity		IEC 93	[Ω]	10 <sup>13</sup>
Comparative Tracking Index (CTI)	Solution A	IEC 112	[V]	600
<b>BURNING BEHAVIOUR</b>				
Flammability	0,8 mm	UL 94	[Class]	V0
Glow Wire Flammability Index (GWFI)	1 - 3 mm	IEC 60695-2-12	[°C]	960
Burning rate (FMVSS)		FMVSS 302	[mm/min]	< 100

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products

#### PROCESSING CONDITIONS:

Drying temperature/time	: 75-85°C/4-6h
Recommended melt temperature	: 260-290 °C
Recommended mould temperature	: 90 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.