

POLYMERS

SABIC[®] HDPE Bimodal Blown Film FI0750

PRODUCT DESCRIPTION

FI0750 is high molecular weight high density polyethylene copolymer grade specifically designed for blown film applications. The design of the product, molecular architecture and density, gives it a unique combination of easy extrusion and high melt strength with strong physical properties which makes it suitable for producing thin films with excellent strength and rigidity.

TYPICAL APPLICATIONS

FI0750 is recommended for blown film extrusion. It can be used for producing grocery sacks, shopping bags, refuse bags, thin films for bag on roll, wrapping film and also for replacement of thin paper products. Films produced with this product can be readily treated and printed to give high quality graphics.

TYPICAL DATA

PROPERTIES	Unit	Value ⁽¹⁾	Test Method
Melt Flow Rate			
@ 190°C & 5 kg load	g/10 min	0.22	ISO 1133
@ 190°C & 21.6 kg load		7.5	
Density @ 23°C	Kg/m ³	950	ISO 1183
MECHANICAL PROPERTIES ⁽²⁾			
Tensile Strength@ yield, MD, TD	MPa	50 , 45	ISO 527
Tensile elongation @ Break MD, TD	%	400 , 450	ISO 527
Dart Impact Strength, F50	g	240	ASTM D 1709
Elmendorf Tear Strength, MD, TD	mN	250 , 450	ISO 6383-2
Hardness (Shore D)	-	62	ISO 868
THERMAL PROPERTIES			
Vicat Softening Point	°C	75	ISO 306
Brittleness Temperature	°C	< -80	ASTM D 746

(1) Typical values: not to be construed as specification limits.

(2) Properties are based on 20 µm film produced at 4 BUR using 100% FI0750.

Processing Conditions:
Melt Temperature: 200-225°C
Frost line Height: 6-8 times die Ø
BUR: 3-5

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, Additional specific information can be requested via your local Sales Office.

STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation,
P.O. Box 5101, Riyadh 11422,
Kingdom of Saudi Arabia
Tel: 966 11 2258000
Fax: 966 11 2259000
Website: www.sabic.com

Technical Marketing
Tel: 966 11 2503093

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.

© 2013 Copyright by SABIC. All rights reserved