



GREENFLEX®

FD 50

EVA

Ethylene vinyl acetate copolymer

Greenflex FD 50 is an ethylene vinyl acetate copolymer (EVA) for blown film extrusion.

Films produced by Greenflex FD 50 exhibit good optical and sealing properties, high flexibility and toughness.

Main Application

Greenflex FD 50 is recommended for the production of agricultural films and water proofing membrane having outstanding mechanical performances (flexibility, elasticity and adherence) and dimensional stability.

Main Properties

Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	0.4	g/10min	ISO 1133
Vinyl acetate content	17	%	Internal method
Density	0.938	g/cm ³	ISO 1183
Melting Point	88	°C	Internal method
Brittleness temperature	<- 80	°C	ASTM D 746
Vicat softening point (1 kg)	67	°C	ISO 306/A

Film Properties *	Value	Unit	Test Method
Tensile stress at yield MD	4.5	MPa	ISO 527-3
Tensile stress at yield TD	4	MPa	ISO 527-3
Tensile stress at break MD	35	MPa	ISO 527-3
Tensile stress at break TD	30	MPa	ISO 527-3
Elongation at break MD	450	%	ISO 527-3
Elongation at break TD	700	%	ISO 527-3
1% Secant modulus MD	55	MPa	ISO 527-3
1% Secant modulus TD	60	MPa	ISO 527-3
Elmendorf tear resistance MD	20	N/mm	ISO 6383-2
Elmendorf tear resistance TD	44	N/mm	ISO 6383-2
Impact resistance F50 (Dart Drop Test)	> 700	g	ISO 7765-1/A
Dynamic coefficient of friction (COF)	> 0.5	-	ISO 8295
Haze	1.5	%	ISO 14782
Gloss, 45°	83	%	ASTM D 2457
Recommended film thickness	30 ÷ 150	micron	-

Film Properties **	Value	Test Method
ShoreA:	90	ISO 868 A
ShoreD:	39	ISO 868 A

(*) Film properties are typical of a blown film extruded at 200 C°. Actual properties may vary depending upon operating conditions and additive package.

** values are referred to injection moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

Processing notes

Greenflex FD 50 can be processed by conventional blown film extrusion equipments. A stock temperature from 160°C to 190°C is recommended. Depending on extrusion conditions, the suggested film thickness is 50÷200 µm.

Storage and Handling

Greenflex FD 50 is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Greenflex FD 50 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications.

Certificates of compliance are available upon request.

TECHNICAL SERVICE

versalis S.p.A.
Piazza Boldrini, 1
20097 S.Donato Milanese, Italia
Tel. +39 02 520.32087
Fax +39 02 520.52052

Versalis International SA
succursale française
Port 4531 Route des Dunes - BP
59
F-59279 Mardyck

versalis S.p.A.
Via Taliercio, 14
46100 Mantova, Italia
Tel. +39 0376 305667
Fax +39 02 52043

HEADQUARTER

versalis S.p.A.
Piazza Boldrini, 1
20097 S.Donato Milanese, Italia
Tel. +39 02 520.32087
Fax +39 02 520.52052

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

versalis is available to provide the guaranteed values for each product on demand.