



HP0722N

Low Density Polyethylene for Blown Film

Product Description

HP0722N is Low Density Polyethylene grade suitable for producing medium duty films and contains no slip and antiblock additives. It gives good toughness and optical properties in the film.

Typical Applications

HP0722N can be used for medium duty bags, shrink films, shopping bags, lamination films and frozen food packaging.

Typical data

Properties	Unit	Value ⁽¹⁾	Test Method
Melt Flow Rate @190°C & 21.6 kg load	g/10 min.	0.75	D 1238
Density @ 23°C	kg/m ³	922	D 1505
Mechanical Properties(2)			
Tensile Strength @ break, MD TD	MPa	27 23	D 882
Tensile Elongation @ break, MD TD	%	400	D 882
Tensile Strength @ yield, MD TD	MPa	650 10	D 882
1% Secant Modulus, MD TD	MPa	9 180	D 882
Dart Impact Strength	g	200 200	D 1709
Elmendorf Tear Strength, MD TD	g	350 280	D 1922
Optical Properties(2)			
Haze	%	9	D 1003
Gloss @ 45°	-	60	D 2457
Thermal Properties			
Vicat Softening Point	°C	95	D 1525

(1) Typical values; not to be construed as specification limits.

(2) Properties have been measured by producing 50 µ film with 2.5 BUR using 100% HP0722N.

Product Description

Typical processing conditions for HP0722N are:

Melt temperature: 170 - 185°C

Blow up ratio: 2.5 - 4.0

Food Regulation

HP0722N is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local Representative for certificate.

Storage and Handling

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia

Tel: 966 1 2258000

Fax: 966 1 2259000

Technical Marketing

Tel: 966 1 2659166

Fax: 966 1 2653544

Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.