



HP2022 Series

Low Density Polyethylene for Blown Film

Product Description

HP2022 series resins are Low Density Polyethylene grades suitable for general purpose packaging. They exhibit better draw down, good opticals and mechanical properties.

Typical Applications

Thin shrink film, lamination film, produce bags, textile packaging, soft goods packaging, general purpose bags with good optics and t-shirts carrier bags.

HP2022N: No Slip & No Antiblock

HP2022J: 750 ppm Slip & 1000 ppm Antiblock

Typical data

Properties	Unit	Value ⁽¹⁾	Test Method
Melt Flow Rate @190°C & 21.6 kg load	g/10 min.	0.75	D 1238
Density @ 23°C	kg/m3	922	D 1505
Mechanical Properties(2)			
Tensile Strength @ break, MD TD	MPa	21 18	D 882
Tensile Elongation @ break, MD TD	%	290 570	D 882
Tensile Strength @ yield, MD TD	MPa	8 7	D 882
1% Secant Modulus, MD TD	MPa	160 180	D 882
Dart Impact Strength	g	80 180	D 1709
Elmendorf Tear Strength, MD TD	g	150	D 1922
Optical Properties(2)			
Haze	%	7	D 1003
Gloss @ 45°	-	80	D 2457
Thermal Properties			
Vicat Softening Point	°C	92	D 1525

(1) Typical values; not to be construed as specification limits.

(2) Properties have been measured by producing 30 µ film with 2.5 BUR using 100% HP2022N.

Product Description

Typical processing conditions for HP2022 are:

Melt temperature: 160 - 180°C

Blow up ratio: 2 - 3

Food Regulation

HP2022 series resins are suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

Storage and Handling

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia
Tel: 966 1 2258000
Fax: 966 1 2259000

Technical Marketing
Tel: 966 1 2659166
Fax: 966 1 2653544
Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.