

KOPELEN J-380A

PP BLOCK COPOLYMER

General Information

Description

J-380A is high impact block copolymer which has high ethylene-propylene rubber content. This grade is designed to be processed in huge Injection molding equipments by improvement in mold release and anti-static. J-380A show high melt flow and has good balance of strength, impact resistance.

Applications

- General household goods, thin-wall parts
- Home appliances etc.

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ASTM D1238	60	g/10min		
Density	ASTM D792	0.90	g/cm ³		
Mechanical					
Tensile Stress (Yield)	ASTM D638	240	kgf/cm ²	23	MPa
Tensile Strain (Break)	ASTM D638	>10	%	>10	%
Flexural Modulus	ASTM D790	15,000	kgf/cm ²	1,470	MPa
Impact					
Notched Izod Impact Strength (23 °C)	ASTM D256	5.0	kgf-cm/cm	49	J/m
Notched Izod Impact Strength (-10 °C)	ASTM D256	2.5	kgf-cm/cm	25	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm ²)	ASTM D648	125	°C		
Additional Properties					
Flammability	UL94	HB			

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

KOPELEN J-380A

PP BLOCK COPOLYMER

General Information

Description

J-380A is high impact block copolymer which has high ethylene-propylene rubber content. This grade is designed to be processed in huge Injection molding equipments by improvement in mold release and anti-static. J-380A show high melt flow and has good balance of strength, impact resistance.

Applications

- General household goods, thin-wall parts
- Home appliances etc.

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ISO 1133	60	g/10min		
Density	ISO 1183	0.90	g/cm ³		
Mechanical					
Tensile Stress (Yield)	ISO 527-1	230	kgf/cm ²	23	MPa
Tensile Strain (Break)	ISO 527-1	<100	%	<100	%
Flexural Modulus	ISO 178	13,000	kgf/cm ²	1,270	MPa
Impact					
Notched Izod Impact Strength (23 °C)	ISO 180	4.5	kgf-cm/cm	44	J/m
Notched Izod Impact Strength (-10 °C)	ISO 180	2	kgf-cm/cm	20	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm ²)	ISO 75-1	105	°C		
Additional Properties					
Flammability	UL94	HB			

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications