

POLYMERS

SABIC[®] HDPE Injection Molding M200056

PRODUCT DESCRIPTION

M200056 is High Density Polyethylene grade with narrow molecular weight distribution suitable for injection molding applications. It has been designed to give good flow properties, low warpage with good dimensional stability and high gloss.

TYPICAL APPLICATIONS

M200056 is recommended for housewares, food containers, toys, caps and closures etc.

TYPICAL DATA

PROPERTIES	Unit	Value ⁽¹⁾	Test Method
Melt Flow Rate			
@ 190°C & 2.16 kg load	g/10 min	20	ASTM D1238
Density @ 23°C	Kg/m ³	956	ASTM D1505
MECHANICAL PROPERTIES ⁽²⁾			
1% Secant Modulus	MPa	800	ASTM D 638
Tensile Strength @ Yield	MPa	24	ASTM D 638
Tensile Strength @ Break	MPa	12	ASTM D 638
Tensile Elongation @ Break	%	>200	ASTM D 638
Flexural Strength	MPa	23	ASTM D 790
Flexural Modulus	MPa	825	ASTM D 790
Izod Impact	J/m	30	ASTM D 256
Hardness (Shore D)	-	60	ASTM D 2240
ESCR (100% Igepal), F50*	Hrs	3	ASTM D 1693B
ESCR (10% Igepal), F50*	Hrs	2	ASTM D 1693B
THERMAL PROPERTIES			
Vicat Softening Point	°C	124	ASTM D 1525
Brittleness Temperature	°C	< -75	ASTM D 746

(1) Typical values: not to be construed as specification limits.

(2) Based on Injection molded specimens.

*Based on compression molded sheet

Processing Conditions:

Typical processing conditions for M200056 are:

Barrel temperature: 180-250°C (356-480°F)

Mold temperature: 15-60°C (60-140°F)

Injection pressure: 600-1000 Bar (8700-14500 psi)

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, Additional specific information can be requested via your local Sales Office.

STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation,
P.O.Box 5101, Riyadh 11422,
Kingdom of Saudi Arabia
Tel: 966 11 2258000
Fax: 966 11 2259000
Website: www.sabic.com

Technical Marketing
Tel: 966 11 2503093

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.

© 2013 Copyright by SABIC. All rights reserved