

POLYMERS

SABIC[®] HDPE Injection Molding M80064 Series

PRODUCT DESCRIPTION

M80064 is High Density Polyethylene grade with narrow molecular weight distribution suitable for injection molding applications. It has been designed to give good rigidity, toughness and low warpage. M80064 is also available with UV stabilizer as M80064S.

TYPICAL APPLICATIONS

M80064 series grades are recommended for crates, molded cases and trays, industrial pails and other similar products requiring toughness and rigidity.

TYPICAL DATA

PROPERTIES	Unit	Value ⁽¹⁾	Test Method
Melt Flow Rate			
@ 190°C & 2.16 kg load	g/10 min	8	ASTM D 1238
Density @ 23°C	Kg/m ³	964	ASTM D 1505
MECHANICAL PROPERTIES ⁽²⁾			
1% Secant Modulus	MPa	950	ASTM D 638
Tensile Strength @ Yield	MPa	26	ASTM D 638
Tensile Strength @ Break	MPa	18	ASTM D 638
Tensile Elongation @ Break	%	>800	ASTM D 638
Flexural Strength	MPa	25	ASTM D 790
Flexural Modulus	MPa	1000	ASTM D 790
Izod Impact	J/m	75	ASTM D 256
Hardness (Shore D)	-	62	ASTM D 2240
ESCR (100% Igepal), F50*	Hrs	3	ASTM D 1693B
ESCR (10% Igepal), F50*	Hrs	2	ASTM D 1693B
THERMAL PROPERTIES			
Vicat Softening Point	°C	125	ASTM D 1525
Brittleness Temperature	°C	< -75	ASTM D 746

(1) Typical values: not to be construed as specification limits.

(2) Based on Injection molded specimens.

*Based on compression molded sheet

Processing Conditions:

Typical processing conditions for M80064 are:

Barrel temperature: 200-250°C (390-480°F)

Mold temperature: 15-60°C (60-140°F)

Injection pressure: 600-1000 Bar (8700-14500 psi)

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, Additional specific information can be requested via your local Sales Office.

STORAGE AND HANDLING

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation,
P.O. Box 5101, Riyadh 11422,
Kingdom of Saudi Arabia
Tel: 966 11 2258000
Fax: 966 11 2259000
Website: www.sabic.com

Technical Marketing
Tel: 966 11 2503093

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.

© 2013 Copyright by SABIC. All rights reserved