

POPELEN HCA-352S

PP BLOCK COPOLYMER

General Information

● Characteristics

High Stiffness, High Impact Strength

● Applications

Automotive Parts (Pillar, Console).

물성 항목¹

Physical	Test Method	Unit	Nominal Values
Melt Flow Index (230 °C)	ASTM D1238	g/10min	9.0
Density	ASTM D792	g/cm ³	1.04
Mechanical			
Yield Strength	ASTM D638	kgf/cm ²	350
Elongation	ASTM D638	%	20
Flexural Modulus	ASTM D790	kgf/cm ²	27,000
Flexural Strength	ASTM D790	kgf/cm ²	480
IZOD Impact Strength (23 °C)	ASTM D256	kgf·cm/cm	6.0
IZOD Impact Strength (-10 °C)	ASTM D256	kgf·cm/cm	3.0
Rockwell Hardness	ASTM D785	R	100
Thermal			
Heat Distortion Temp. (4.6kgf/cm ²)	ASTM D648	°C	140

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications