

POPELEN HIP-372

PP BLOCK COPOLYMER

General Information

● Characteristics

Paintability, High Impact Strength

● Applications

Automotive Parts (Crash Pad)

Physical Properties¹

Physical	Test Method	Unit	Nominal Values
Melt Flow Index (230 °C)	ASTM D1238	g/10min	12.0
Density	ASTM D792	g/cm ³	1.06
Mechanical			
Yield Strength	ASTM D638	kgf/cm ²	260
Elongation	ASTM D638	%	150
Flexural Modulus	ASTM D790	kgf/cm ²	25,000
Flexural Strength	ASTM D790	kgf/cm ²	400
IZOD Impact Strength (23 °C)	ASTM D256	kgf·cm/cm	22.0
IZOD Impact Strength (-10 °C)	ASTM D256	kgf·cm/cm	6.0
Pensile Hardness			4B
Thermal			
Heat Distortion Temp. (4.6kgf/cm ²)	ASTM D648	°C	135

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications