

General Information

Description

SEETEC VE800 resin is produced by ExxonMobil Chemical's autoclave process technology. SEETEC VE800 resin, with 28% VA content, is an excellent raw material in the application of solar cell encapsulants.

Additives

- ◆ None

Applications

- ◆ Solar cell encapsulants
- ◆ Hot melt adhesives

Physical Properties¹

Properties	Nominal Value	Unit	Test Method
Melt Index	25.0	g/10min	ASTM D1238
Vinyl Acetate	28	wt.%	LC Method
Density	0.950	g/cm ³	ASTM D1505
Melting Point	69	°C	LC Method
Hardness	25	D scale	ASTM D2240
Vicat Softening Point	< 50	°C	ASTM D1525

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications