

U8835

LINEAR LOW DENSITY POLYETHYLENE

General Information

- Description
 - U8835 is a linear low density polyethylene extrusion coating grade especially designed for the tarpaulin extrusion coating application providing good heat sealing, good drawdownability.
- Additives
 - Antioxidant
- Applications
 - Tarpaulin Extrusion Coating

Physical Properties ¹				
Properties	Test Method		Nominal Value	
Melt Index, at 190 ℃ /2.16kg	ASTM D 1238	14	g/10min	
Density	ASTM D 1505	0.923	g/cm ³	
VICAT Softening Point	ASTM D 1525	94	°C	
Neck-in 50m/min, 315 °C	LC Method	5.8	cm	
150m/min, 315°C		4.7	GIII	
Minimum coating weight	LC Method	7	g/m²	

Note	ISO 9001, 14001, /TS 16949

¹ Physical Properties: these are not to be construed as specifications

www.lottechem.com